



## AFM 34

---

### AFM 34

#### Technical Data Sheet 334

Edition: 11/2018, supersedes all prior editions.

Please see the latest issue under [www.reinz-industrial.com](http://www.reinz-industrial.com)

<b>Material</b>	<b>AFM 34</b> is an asbestos- free gasket material. It contains aramide fibers, inorganic fillers and other high- temperature resistant substances which are bonded with high strength and especially gas- tight under increased pressure and increased temperature.
<b>Properties</b>	<p><b>AFM 34</b> does not contain any physiologically harmful substances or colour pigments.</p> <p><b>AFM 34</b> exhibits high tensile strength plus stress and shearing resistance. The material is ideally suited for sealing gases and fluids, e.g. oils, solvents, fuels, Freons, liquid gases, water/ antifreeze mixtures, saline solutions and many other media. It is also suitable for sealing hot water and steam up to approx. 200 °C in stationary applications and with an installation surface pressure of at least 50 N/ mm<sup>2</sup>. Please consult us if you have a specific application.</p> <p>Other characteristic properties of the material are excellent temperature resistance, stress resistance under high operating pressure, and ease of handling.</p>
<b>Application</b>	<ul style="list-style-type: none"><li>• for DIN and ANSI flanged joints, apparatus, pumps, fittings and pipelines in industrial plants</li><li>• for fittings with very narrow sealing surfaces, e.g. in gas and hot water units, solar panels, convection radiators and couplings, etc.</li><li>• for sealed joints in IC engines subject to high mechanical and thermal stress (oil filters, intake manifolds, water, fuel &amp; vacuum pumps, etc.)</li><li>• for transmissions, gearboxes, refrigerating &amp; air compressors, etc.</li></ul> <p>Since <b>AFM 34</b> is physiologically safe, it is also suitable for use in contact with drinking water &amp; foodstuffs, and for sealing highly pure, pollutant-sensitive products such as paint bases, vitamins, etc.</p>
<b>Surfaces</b>	<p>As standard, both sides of <b>AFM 34</b> are coated with a non- stick, high-friction layer that greatly facilitates disassembly. In most cases, additional surface treatment is unnecessary.</p> <p>However, a graphite coating on one or both sides of the gasket is recommended when used with components that rotate on the gasket during assembly, e.g. in threaded couplings, radiator plugs, etc., as a low friction value is required in these cases.</p>



## AFM 34

---

### Approvals

#### **DIN- DVGW**

(acc. to DIN 3535, part 6 FA)

#### **FDA- compliant**

acc. to 21 CFR § 177.2600 – suitable for flat gaskets with all types of foodstuffs

#### **WRAS**

Certification of gasket materials for use in drinking water (acc. to British Standard BS 6920)

#### **DIN 30653 (formerly VP 401)**

Gaskets with higher thermal resistance (HTB)

#### **Fire Safe**

acc. to BS 6755 and API 6FB

#### **BAM**

German Federal Institute for Materials Research and Testing, flanged joints in oxygen- conducting steel pipes up to 100 bar and 80 °C

#### **Grade X**

acc. to BS 7531

#### **UVV 61**

"Gases", AD- B7 (VdTÜV) in conjunction with metal inner eyelet, blowout-proof gasket

#### **TA Luft**

High- quality gasket (200 °C for 48 h and 2000 h)

#### **Germanischer Lloyd (DNV GL)**

Approval for shipbuilding



## AFM 34

### Technical Data

(nominal thickness 2.00 mm)

<b>Density</b>	g/ cm <sup>3</sup>	1.8 - 2.0
<b>Ignition loss acc to DIN 52 911</b>	%	< 34
<b>Tensile strength</b>		
acc. to ASTM F 152 accross gain	N/ mm <sup>2</sup>	> 18
acc. to DIN 52 910 accross gain	N/ mm <sup>2</sup>	> 12
<b>Residual stress acc. to DIN 52 913</b>		
16 h, 300 °C	N/ mm <sup>2</sup>	≈ 25
16 h, 175 °C	N/ mm <sup>2</sup>	≈ 36
<b>Compressibility and recovery</b>		
acc. to ASTM F 36, procedure J		
compressibility	%	5 - 8
recovery	%	> 55
<b>Sealability against nitrogen</b>		
acc. to DIN 3535, part 6 FA	mg/ (s·m)	≈ 0.02
<b>Swelling acc. to ASTM F 146</b>		
<b>in IRM 903 Oil</b> (replaces ASTM Oil No. 3)		
5 h, 150 °C		
increase in thickness	%	< 7
increase in weight	%	< 7
<b>in ASTM Fuel B</b>		
5 h, room temp.		
increase in thickness	%	< 10
increase in weight	%	< 10
<b>in water / antifreeze (50:50)</b>		
5 h, 100 °C		
increase in thickness	%	< 10
increase in weight	%	< 10
<b>Content of water- soluble chloride</b>	ppm	< 100
<b>Thermal conductivity</b>	W/ (m·K)	≈ 0.7
<b>Dielectric strength</b>		
after storage at 50% relative humidity, 48 h	kV/ mm	≈ 20
at 300 °C, 4 h	kV/ mm	≈ 30
<b>Electrical specific resistance</b>		
after storage at 55% relative humidity, 48 h	Ω·cm	≈ 1 x 10 <sup>12</sup>
at 120 °C, 1 h	Ω·cm	≈ 2 x 10 <sup>13</sup>
<b>Short- term peak temperature</b>	°C	400
<b>Maximum continuous temperature</b>	°C	250
with steam up to	°C	200
with metal inner bead (AFM 34 CO ME)		
with steam up to	°C	220
<b>Maximum operating pressure</b>	bar	150



**Max. continuous temperature and max. pressure must not occur simultaneously, please refer to the table entitled "Max. operating pressures at various temperatures and with various media".**

## AFM 34

<b>DIN 28091-2:</b>		
<b>Cold creep</b> $\epsilon_{KSW}$	%	5 - 8
<b>Cold recovery</b> $\epsilon_{KRW}$	%	3 - 5
<b>Hot creep during service</b> $\epsilon_{WSW/T}$	%	9 - 12
<b>Hot recovery</b> $\epsilon_{WRW/T}$	%	≈ 0,9
<b>Recovery R</b>	mm	≈ 0,016
<b>Specific leakage rate</b> $\lambda$	mg / (s·m)	< 0,1
<b>Media resistance</b>		
see " <a href="#">AFM 34: Resistance to chemical media</a> "		
<b>Residual surface pressure</b> after 1000 h (in air at 100 °C)	%	> 50

**Sealing parameters:** see corresponding [table](#).  
Characteristics acc. to EN 13555 are available on request.



The data quoted above are valid for the material "as delivered" without any additional treatment. In view of the countless possible installation and operating conditions, definitive conclusions cannot be drawn for all applications regarding the behaviour in a sealed joint. Therefore, we do not give any warranty for technical data, as they do not represent assured characteristics. If you have any doubt, please contact us and specify the exact operating conditions.

### Form of delivery

<b>Gaskets</b>	according to a drawing, dimensions supplied, or other arrangement.
<b>Sheets</b>	1500 x 1500 mm (standard size)

**Nominal thicknesses and tolerances** acc. to DIN 28091-1 (mm)  
Dimensional limits within a shipment

<b>0.30</b>	±0.10
<b>0.50</b>	±0.10
<b>0.75</b>	±0.10
<b>1.00</b>	±0.10
<b>1.50</b>	±0.15
<b>2.00</b>	±0.20
<b>3.00</b>	±0.30
<b>4.00</b>	±0.40
<b>5.00</b>	±0.50

Max. thickness variation in a sheet:  
0.1 mm for sheet thickness ≤ 1.00 mm, and 0.2 mm for thickness > 1.00 mm