
**AFM 34 Metall****AFM 34 Metall****Technical Data Sheet 134 (previously TD 279)**

Edition: 07/2025, supersedes all prior editions.

Please see the latest issue under [www.reinz-industrial.com](http://www.reinz-industrial.com)

<b>Material</b>	<b>AFM 34 METALL</b> is an asbestos- free gasket material with a strong reinforcement of expanded stainless steel 1.4404 (316L) which is 0.5 mm thick. The material is physiologically safe and contains no color pigments. It is composed of aramide fibers and other asbestos substitutes which are resistant to high temperatures and are processed with high- grade elastomers under elevated pressure and temperature.
<b>Properties</b>	<p><b>AFM 34 METALL</b> is resistant to media such as oils, solvents, fuels, steam, saline solutions, refrigerating agents (freons), alcohols, and many others.</p> <p>Due to the expanded metal mesh reinforcement, the gasket material features a number of outstanding properties as compared to conventional composite materials. <b>AFM 34 METALL</b> exhibits very high tensile strength, high stress and shear resistance, and is extremely easy to handle. <b>AFM 34 METALL</b> exhibits far lower values for hot creep than conventional composite materials.</p> <p>The expanded metal mesh reinforcement permits <b>AFM 34 METALL</b> to cope better with higher pressures and temperatures than conventional non- reinforced materials. It is also suitable for sealing hot water and steam up to 200 °C in stationary applications and with an installation surface pressure of at least 75 N/ mm<sup>2</sup>. Please consult us if you have a specific application.</p> <p>In spite of its expanded metal reinforcement, the gasket material exhibits high sealability with gases – a novel feature with metal- reinforced fiber gasket materials.</p>
<b>Application</b>	<ul style="list-style-type: none"><li>• for DIN and ANSI flanges, fittings, pumps and apparatus in chemical plants, refineries, power stations as well as in shipbuilding and in high- pressure gas supply plants and refrigeration engineering</li><li>• in general for sealed joints in which high mechanical and/ or thermal stresses or alternating loads occur</li><li>• for sealing components with relatively narrow lands, e.g. heat exchangers, steam fittings, air and refrigerating compressors as well as all threaded couplings</li><li>• also suitable for sealed joints subject to high mechanical stress in IC engines, e.g. for sealing intake manifolds and timing cases.</li></ul>
<b>Surfaces</b>	As standard, both sides of <b>AFM 34 METALL</b> are coated with a non- stick, high- friction layer that greatly facilitates disassembly. In most cases, additional surface treatment is unnecessary.



**AFM 34 Metall**

**Technical Data**  
(nominal thickness  
1.0 mm)

<b>Density</b>	g/ cm <sup>3</sup>	≈ 2.6
<b>Ignition loss</b> acc. to DIN 52 911	%	< 22
<b>Tensile strength</b> across grain	N/ mm <sup>2</sup>	> 60
with grain	N/ mm <sup>2</sup>	> 33
<b>Residual stress</b> acc. to DIN 52 913 16 h, 300 °C	N/ mm <sup>2</sup>	≈ 42
16 h, 175 °C	N/ mm <sup>2</sup>	≈ 46
<b>Compressibility and recovery</b> acc. to ASTM F 36, procedure J compressibility	%	≈ 5
recovery	%	≈ 60
<b>Sealability</b> against nitrogen acc. to DIN 3535, part 6 FA	mg/ (s·m)	≈ 0.05
<b>Swelling</b> acc. to ASTM F 146		
<b>in IRM 903 Oil</b> (replaces ASTM Oil No. 3) 5 h, 150 °C		
increase in thickness	%	< 10
increase in weight	%	< 10
<b>in ASTM Fuel B</b> 5 h, room temp.		
increase in thickness	%	< 10
increase in weight	%	< 10
<b>in water / antifreeze (50:50)</b> 5 h, 100 °C		
increase in thickness	%	< 5
increase in weight	%	< 5
<b>Content of water- soluble chloride</b>	ppm	< 100
<b>Minimum installed surface pressure</b> $\sigma_{VU/L}$ for sealing against helium acc. to Reinz Test Method RPM 505: Leakage rate 10-2 mbar·l/ s·m = 0.6 cm <sup>3</sup> / min·m		
at 10 bar	N/ mm <sup>2</sup>	60
at 25 bar	N/ mm <sup>2</sup>	80
at 50 bar	N/ mm <sup>2</sup>	100
<b>Short- term peak temperature</b>	°C	400
<b>Maximum continuous temperature</b>	°C	275
for steam up to	°C	240
<b>Maximum operating pressure</b>	bar	300



**Max. continuous temperature and max. pressure must not occur simultaneously, please refer to the table entitled "Max. operating pressures at various temperatures and with various media"!**



The data quoted above are valid for the material "as delivered" without any additional treatment. In view of the countless possible installation and operating conditions, definitive conclusions cannot be drawn for all applications regarding the behaviour in a sealed joint. Therefore, we do not give any warranty for technical data, as they do not represent assured characteristics. If you have any doubt, please contact us and specify the exact operating conditions.



**AFM 34 Metall**

**Technical Data**  
(nominal thickness 1.5 mm)

<b>Density</b>	g/ cm <sup>3</sup>	≈ 2.45
<b>Ignition loss</b> acc. to DIN 52 911	%	< 24
<b>Tensile strength</b> across grain	N/ mm <sup>2</sup>	> 52
with grain	N/ mm <sup>2</sup>	> 33
<b>Residual stress</b> acc. to DIN 52 913 16 h, 300 °C	N/ mm <sup>2</sup>	≈ 33
16 h, 175 °C	N/ mm <sup>2</sup>	≈ 43
<b>Compressibility and recovery</b> acc. to ASTM F 36, procedure J		
compressibility	%	≈ 5
recovery	%	≈ 60
<b>Sealability</b> against nitrogen acc. to DIN 3535, part 6 FA	mg/ (s·m)	≈ 0.05
<b>Swelling</b> acc. to ASTM F 146		
<b>in IRM 903 Oil</b> (replaces ASTM Oil No. 3) 5 h, 150 °C		
increase in thickness	%	< 10
increase in weight	%	< 10
<b>in ASTM Fuel B</b> 5 h, room temp.		
increase in thickness	%	< 10
increase in weight	%	< 10
<b>in water / antifreeze</b> (50:50) 5 h, 100 °C		
increase in thickness	%	< 5
increase in weight	%	< 5
<b>Content of water- soluble chloride</b>	ppm	< 100
<b>Minimum installed surface pressure</b> $\sigma_{VU/L}$ for sealing against helium acc. to Reinz Test Method RPM 505: Leakage rate 10-2 mbar·l/ s·m = 0.6 cm <sup>3</sup> / min·m		
at 10 bar	N/ mm <sup>2</sup>	45
at 25 bar	N/ mm <sup>2</sup>	60
at 50 bar	N/ mm <sup>2</sup>	80
<b>Short- term peak temperature</b>	°C	400
<b>Maximum continuous temperature</b>	°C	260
for steam up to	°C	240
<b>Maximum operating pressure</b>	bar	250



**Max. continuous temperature and max. pressure must not occur simultaneously, please refer to the table entitled "Max. operating pressures at various temperatures and with various media"!**



The data quoted above are valid for the material "as delivered" without any additional treatment. In view of the countless possible installation and operating conditions, definitive conclusions cannot be drawn for all applications regarding the behaviour in a sealed joint. Therefore, we do not give any warranty for technical data, as they do not represent assured characteristics. If you have any doubt, please contact us and specify the exact operating conditions.




**AFM 34 Metall**

**Technical Data**  
(nominal thickness 2.0 mm)

<b>Density</b>	g/ cm <sup>3</sup>	≈ 2.3
<b>Ignition loss</b> acc. to DIN 52 911	%	< 26
<b>Tensile strength</b> across grain	N/ mm <sup>2</sup>	> 45
with grain	N/ mm <sup>2</sup>	> 33
<b>Residual stress</b> acc. to DIN 52 913 16 h, 300 °C	N/ mm <sup>2</sup>	≈ 25
16 h, 175 °C	N/ mm <sup>2</sup>	≈ 40
<b>Compressibility and recovery</b> acc. to ASTM F 36, procedure J compressibility	%	≈ 5
recovery	%	≈ 60
<b>Sealability</b> against nitrogen acc. to DIN 3535, part 6 FA	mg/ (s·m)	≈ 0.05
<b>Swelling</b> acc. to ASTM F 146		
<b>in IRM 903 Oil</b> (replaces ASTM Oil No. 3) 5 h, 150 °C		
increase in thickness	%	< 10
increase in weight	%	< 10
<b>in ASTM Fuel B</b> 5 h, room temp.		
increase in thickness	%	< 10
increase in weight	%	< 10
<b>in water / antifreeze</b> (50:50) 5 h, 100 °C		
increase in thickness	%	< 5
increase in weight	%	< 5
<b>Content of water- soluble chloride</b>	ppm	< 100
<b>Minimum installed surface pressure</b> $\sigma_{vu/L}$ for sealing against helium acc. to Reinz Test Method RPM 505: Leakage rate 10-2 mbar·l/ s·m = 0.6 cm <sup>3</sup> / min·m		
at 10 bar	N/ mm <sup>2</sup>	34
at 25 bar	N/ mm <sup>2</sup>	45
at 50 bar	N/ mm <sup>2</sup>	60
<b>Short- term peak temperature</b>	°C	400
<b>Maximum continuous temperature</b>	°C	250
for steam up to	°C	240
with metal inner eyelet (ME)		
for steam up to	°C	275
<b>Maximum operating pressure</b>	bar	200



**Max. continuous temperature and max. pressure must not occur simultaneously, please refer to the table entitled "Max. operating pressures at various temperatures and with various media"!**



**AFM 34 Metall**

**DIN 28091-2:**

<b>Cold creep</b> $\epsilon_{KSW}$	%	5 - 8
<b>Cold recovery</b> $\epsilon_{KRW}$	%	2 - 4
<b>Hot creep during service</b> $\epsilon_{WSW/T}$	%	4 - 7
<b>Hot recovery</b> $\epsilon_{WRW/T}$	%	≈ 0.60
<b>Recovery R</b>	mm	≈ 0.01
<b>Specific leakage rate</b> $\lambda$	mg/ (s·m)	< 0.1
<b>Residual surface pressure</b> after 1000 h (in air at 100 °C)	%	> 50

**Sealing parameters** see [Table](#)



The data quoted above are valid for the material "as delivered" without any additional treatment. In view of the countless possible installation and operating conditions, definitive conclusions cannot be drawn for all applications regarding the behaviour in a sealed joint. Therefore, we do not give any warranty for technical data, as they do not represent assured characteristics. If you have any doubt, please contact us and specify the exact operating conditions.

**Form of delivery**

**Gaskets** according to a drawing, dimensions supplied, or other arrangement.

**Sheets** 1250 x 1500 mm (standard size)

**Nominal thicknesses and tolerances** acc. to DIN 28091-1 (mm)  
Dimensional limits within a shipment

<b>1.00</b>	±0.10
<b>1.50</b>	±0.15
<b>2.00</b>	±0.20

Max. thickness variation in a sheet:  
0.1 mm for sheet thickness ≤1.00 mm, and 0.2 mm for thickness >1.00 mm